

Confix Fin

Thin bed repair mortar



APPLICATION AREA

Confix Fin is a fine-graded dry mortar specifically designed for repairs, reinforcement and maintenance of concrete in thin layers (max. 10 mm) where strength, low shrinkage and density are crucial.

Examples of use:

- Bonded screeds and repair with a monolithic bond.
- Repair of concrete floors.
- Casting of slopes to drains and drainage.
- Casting of coverings.
- General repair of concrete structures.

TECHNICAL INFORMATION

Confix Fin is a pumpable, cement based, dry mortar with a mix ratio of approx. 1:4 of cement / well graded aggregates up to 1.0 mm and with additives that provide good casting results and workability.

Confix Fin, which is only to be added water, is designed for maximum density, firmness and low shrinkage. If the mortar is to be sprayed, it's preferable to use the wet method.

Confix Fin meets the requirement defined by EN 1504-9 "Products and Systems for the protection and repair of concrete structures: Definitions, requirements, quality control and evaluation of conformity.

General principles for the use of products and systems," and the minimum requirements described in EN 1504-3, ("Structural and non-structural repair") for structural mortars of class R3.

RECOMMENDATIONS

- Do not add water after the mixture has started to set.
- Do not use **Confix Fin** if the bag is damaged or previously opened.
- Do not use **Confix Fin** in thicknesses above 10 mm (use **Confix** or **Confix m/PP-Fiber**).
- Avoid featheredges.

INSTRUCTIONS FOR USE

Preparation

The substrate must be thoroughly cleaned, loose concrete and surface contamination must be removed. Chipping, chiselling or sand blasting might be necessary. Wet the concrete thereafter, preferably the day before, so it can dry up again. Standing surface water must not occur.

Mixing

Smaller quantities can be mixed with a drill and whisk. Larger volumes are mixed with a mortar mixer or agitator mixer. Mixing time; a minimum of 3 minutes. The consistency is regulated by adding water, but be aware that using a higher volume of water than recommended, approx. 3.5 litres per sack of 25 kg, can result in greater shrinkage, reduced firmness and a poor result.

The mortar must be applied no later than 2 hours after mixing has taken place. Never add more water after the bonding process has started.

APPLICATION

The mortar is spread with ordinary mason tools, with a pump or suitable spraying equipment - and compacted well. Use at temperatures between +5°C and +35°C.

Monolithic bonding

To achieve good bonding and transferred adhesion to the substrate, **Confix Fin** can be pasted to the substrate with **Mapepoxy L**. The method is performed wet-on-wet. **Mapepoxy L** is applied to the hardened concrete (substrate) with a brush or with a rubber trowel on smooth surfaces. On larger areas and areas with reinforcement, a hopper gun can also be used. Make sure that **Mapepoxy L** is applied within the adhesive's usage time (depending on temperature). Fresh **Confix Fin** must be applied within the adhesive's open time. If open time is exceeded, cover the adhesive with sand and apply a new layer of adhesive. Bonding of fresh **Confix Fin** to hardened concrete with **Mapepoxy L** can be done at any temperatures when it is appropriate to cast **Confix Fin** without adding antifreeze additives. A more reliable result is obtained if the surface is dry, but some moisture in concrete surface can be tolerated (see separate technical data sheet for **Mapepoxy L**).

Finishing

Finishing is best done to exposed surfaces with the application of the curing compound **Mapecure 1**, **Cur-Imp** or **Mapecure WF-75** immediately after casting, and then wetting from the next day and 3 - 4 days afterwards. Covering with plastic sheeting is also effective and is preferred when the surface has to be treated.

CLEANING

Fresh mortar can be removed from tools and equipment with water. Cured material can be removed mechanically.

CONSUMPTION

Approx. 2 kg per litre of the final, mixed product.

PACKAGING

Confix Fin is supplied in 25 kg sacks.

STORAGE

Confix Fin remains stable for at least 12 months if stored in a dry place in unopened packaging.

SAFETY INSTRUCTIONS FOR PREPARATION AND INSTALLATION

Instructions for the safe use of our products can be found on the latest version of the SDS available from our website www.mapei.no

PRODUCT FOR PROFESSIONAL USE.

WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above - information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application: for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application: in every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the technical data sheet, available from our web site www.mapei.no

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in force at the time of the MAPEI product installation.

The most up-to-date TDS can be downloaded from our website www.mapei.no

ANY ALTERATION TO THE WORDING OR REQUIREMENTS CONTAINED OR DERIVED FROM THIS TDS EXCLUDES THE RESPONSIBILITY OF MAPEI.

All relevant references for the product are available upon request and from www.mapei.no

TECHNICAL DATA (typical values)			
PRODUCT IDENTIFICATION			
Strength class according to EN 1504-3:	R3		
Type:	CC		
Consistency:	powder		
Colour:	grey		
D_{max} (mm):	1.0		
Dry solids content (%):	100		
Chloride content - minimum requirements < 0,05 % - according to EN 1015-17 (%):	≤ 0.05		
Storage:	12 months dry storage in original packaging		
PRODUCT APPLICATION DATA (at +20°C - 50% RH)			
Colour of mixture:	grey		
Mixing ratio:	100 parts of Confix Fin with 14 parts water (3.5 l per 25 kg sack)		
Consistency of mixture:	thixotropic		
Density of mixture (kg/m³):	2 160		
pH of mixture:	> 12		
Application temperature range:	from +5°C to +35°C		
Pot life of mixture:	approx. 2 hours		
FINAL PERFORMANCE (water amount 14 %):			
Mechanical characteristics	Test method	Minimum requirements according to EN 1504-3 for R3 class mortar	Product performance
Compressive strength (N/mm²):	EN 12190	≥ 25 (after 28 days)	8 (after 1 day) 25 (after 7 days) 48 (after 28 days)
Flexural strength (MPa):	EN 196-1	none	> 3 (after 1 day) > 4 (after 7 days) > 6 (after 28 days)
Carbonation resistance:	EN 13295	D _v ≤ reference (MC(0,45))	complies with the requirements
E-modul (GPa):	EN 13412	≥ 15	26.7 (after 28 days)
Bonding to concrete (MC 0.40, w/c = 0.40) acc. to EN 1766 (MPa):	EN 1542	≥ 1.5 (after 28 days)	1.7 (after 28 days)
Capillary absorption (kg/m²·h^{0.5}):	EN 13057	≤ 0.5	< 0.25
Resistance to freeze / thaw cycles with deicing salts measured acc. to EN 1542 (MPa):	EN 13687-1	≥ 1.5 (after 50 cycles)	> 1.8
Fire resistance:	Euroclass	Values declared by manufacturer	A1